



Material	Abrasion	Impact	Temperature in °C		FDA
			min	max	approved
HDP	√√	√√	-20	70-80	yes
Nylon 6	√√√	√√√	-30	120-130	yes
Polyurethane	√√√	√√√	-30	60-70	no

index:

√ = medium

√√ = good

√√√ = very good